

Aegis Solar Films Performance Data Sheet Official Report

Film Model Series Thickness	215N (Translucent) or 216N (White) Frosted Series (Sandblast) 0.14mm	
Peel Adhesives Release Adhesion Initial Tack Application Temperature	0.70 – 1.10kg/inch 0.003kg – 0.005kg/inch 20 Mins/ Ball no. 5 – 7 +8 °C to + 50°C	
Resistance Test Against: Humidity Water Seawater Diesel Fuel Detergent Solution Battery Acid	Conditions: 24hrs at 38°C/100% 24hrs at 32°C 1yr Mid Tide (BS 5609:1986) 1hr at 23°C 8hrs at 65°C 24hrs at 23°C	Results: No effect No effect No effect No effect No effect No effect

Applicable For:

Bathroom/Shower Partition/Glass

Office & Meeting Rooms, Manager's and Directors Room

Privacy for premises where office(s) and customer reception area are nearby or within sight

Privacy for Residential Units

See Annex A for Product View

Official data sheet from PROGRESSHENG HOLDINGS PTE. LTD.

The data should be used as indicative and should not be binding

Annex A:

FROSTED FILM: 215N (Translucent)



FROSTED FILM: 216N (White)

